

## TECHNICAL DATA SHEET

### InterSil Wound Contact Layer

InterSil is a thin, perforated, low adherence, silicone wound contact layer dressing consisting of a nonwoven matrix, coated with a soft silicone layer on both sides. The silicone wound contact layer is protected by a clear embossed LDPE liner on both sides. InterSil forms a protective barrier for granulation tissue to grow undisturbed by frequent changes of the outer absorbent dressing being used. This product allows exudate to pass through it, preventing wound maceration without hindering the function of the absorbent dressing.



### TYPICAL APPLICATION

Designed for the treatment of postoperative wounds, first- and second-degree burns, partial to full thickness wounds, stage I-IV pressure ulcers, and arterial and venous leg ulcers.

### FEATURES AND BENEFITS

- Up to 7-day wear time
- Conformable
- Does not leave any residue in wound bed
- Non-irritating
- Atraumatic removal with minimal epidermal stripping
- Reduces frequency of dressing changes
- Easy application and removal

### PACKAGING

	Size	QTY Per Box
DRESSING	8 x 10 cm	10
DRESSING	10 x 15 cm	10
DRESSING	20 x 30 cm	10

InterSil is presented in a paper/poly pouch for single use and is supplied sterile.



Medical

Issue date: 24 April 2023

## PHYSICAL CHARACTERISTICS

Property	Typical Values <sup>†</sup>
THICKNESS	0.5 ± 0.1 mm
PERFORATION DIAMETER	1.3–1.9 mm
PERFORATION QUANTITY	9.2 holes/cm <sup>2</sup>
OPEN HOLES	≥ 98%
FLUID HANDLING WITH 4 mm FOAM DRESSING	≥ 14 g per 24 hr
MVTR	≥ 3500 g/m <sup>2</sup> per 24 hr
ADHESIVE FORCE	≤ 10 gf/25 mm
POUCH SEAL INTEGRITY	≥ 207 gf/ 25.4 mm
POUCH SEAL INK TEST	No leakage
POUCH SEAL PEEL TEST	Good transfer and clean peel

MVTR, moisture vapor transmission rate.

\*Refer to product specifications for material acceptance limits

## STORAGE AND SHELF LIFE

Three years when stored at 23°C (73°F), 50% relative humidity, out of direct sunlight, in original packaging.

## IMPORTANT

Information on the above characteristics is based upon tests we believe to be reliable. The values given are typical values that vary according to application conditions. The values are intended only as a source of information and are given without guarantee and do not constitute a warranty. Purchasers should independently determine prior to use the suitability of this material for their specific purposes. All Avery Dennison materials described herein are sold subject to Avery Dennison Conditions of Sales, a copy of which is available upon request

To learn more about how our material and adhesive science expertise can help drive your next innovation, call:

**United States:** +1 440 358 2600

**Belgium:** +32 14 40 48 11

**Ireland:** +353 43 3349586

[www.medical.averydennison.com](http://www.medical.averydennison.com)

©2023, Avery Dennison Corporation. Avery Dennison and the triangle logo are registered trademarks of Avery Dennison Corporation. All rights reserved.

GBL-MKT-000170-B



Medical